

CLEVIOS™ P SB 6

Description of Product PEDOT-complex, dispersion in a mixture of anisol and butylacetate, blue liquid

Characteristics¹⁾

	min.	max.	Unit
Solid Content	2.0	3.0	%
Surface resistivity (dried layer)		30	kOhm/sq
Solvent	mixture of anisol and butylacetate		

Technical Data (guide values, not a specification)

Boiling Point > 100°C

1) Information on test methods is available on request.

Storage and Handling **Avoid freezing! Avoid heating !**

Storage and handling are subject to the rules and regulations in the country of use. When stored at temperatures between 5°C and a maximum of 25°C, CLEVIOS™ P SB 6 will remain stable for 6 months from date of production in sealed original containers. After opening the containers must be well closed to prevent the evaporation of solvent which may result in the formation of a non re-dispersible film. Brief heating to max 30°C has no adverse effect on product properties.

Hazards identification See material safety data sheet.

Documentation An inspection document in accordance with EN 10204 is supplied with every commercial order. Inspection documents for samples are supplied on request.

Contact Technical Service Display: Dr. A. Sautter, Phone: +49 (214) 30-21201,
armin.sautter@heraeus.com

Technical Service Capacitor: Dr. U. Merker, Phone: +49 (214) 30-23671,
udo.merker@heraeus.com

Note: **PRELIMINARY SPECIFICATION** (The product described is still under test. Amendments of all technical data are possible. Special care has to be taken while processing.)



Heraeus Deutschland GmbH & Co. KG
Heraeus Epurio
Building B 202, Chempark
51368 Leverkusen, Germany
clevios@heraeus.com
www.clevios.com | www.heraeus.com

The conditions of your use and application of our products, technical assistance and information (whether verbal, written or by way of production evaluations), including any suggested formulations and recommendations, are beyond our control. Therefore, it is imperative that you test our products, technical assistance and information to determine to your own satisfaction whether they are suitable for your intended uses and applications. This application-specific analysis at least must include testing to determine suitability from a technical as well as health, safety, and environmental standpoint. Such testing has not necessarily been done by Heraeus. All information is given without warranty or guarantee. It is expressly understood and agreed that the customer assumes and hereby expressly releases Heraeus from all liability, in tort, contract or otherwise, incurred in connection with the use of our products, technical assistance and information. Any statement or recommendation not contained herein is unauthorized and shall not bind Heraeus. Nothing herein shall be construed as a recommendation to use any product in conflict with patents covering any material or its use. No license is implied or in fact granted under the claims of any patent. In case of order please refer to issue number of this product data sheet. All deliveries are based on the latest issue of the product data sheet and on the latest version of our General Conditions of Sale and Delivery.